



Specifications



Open wiring (top) is unsightly and vulnerable. Panel Shield (bottom) provides neat protection for wiring.

Properties of Materials Used in Wiring Duct

Property	Units	ASTM Test	Noryl®
Specific Gravity		D792	1.10
IZOD	ft-lb/in.	D256	5.0
Flexural Strength	psi	D790	12,800
Flexural Modulus	psi	D790	360,000
Tensile Strength	psi	D638	7,800
Compressive Strength	psi	D695	16,000
Water Absorption	24 hrs-%	D570	0.07
Hardness	Rockwell	D785	R-115
	Duro D	D676	
Dielectric Strength		D149	
60 hertz, 25°C, s/t	vpm		400
Dielectric Constant		D150	
60 hz, dry			2.65
1Mhz, dry			2.64
Volume resistivity	ohm-cm	D257	1017
Heat deflecting (°F@ 264 psi)	°F	D648	212
Flammability			94 V-1

The above information is believed reliable. The user should however check the applicable specifications to verify values.